

EZYCOAT CORSA

DESCRIPTION AND COMPOSITION

Following in the footsteps of Ezycoat decorative, hard wearing and durable paint systems, **Ezycoat Corsa** textured paint has been specifically designed to not only protect but to provide an extra dimension of texture finish in comparison to a normal paint.

Ezycoat Corsa has been developed based on the principals as already adopted for the existing range of Ezycoat Render, Texture, Paint Finishes. Ezycoat Australia has been able to further extend on its already proven track record to produce a series of texture products which have been able to bring together the aesthetic features of troweled on textures with the simplicity of paint application to produce the Ezycoat Textured Paint that is second to no other paintable decorative finish.

Ezycoat Corsa: produces a heavy gritty texture which can be likened to that of a coarse bagged textured finish with the advantage of flexibility, durability and adhesive properties.

USE

Ezycoat Corsa is a specially designed pigmented coating systems for application over such products as EzySkim Render, Ezyump, ECA, Super 6 and Conventional Render. **Ezycoat Corsa** is suitable for application over non-rendered brickwork, blockwork and various other non rendered masonry surfaces.

The final product will produce a protective decorative coating that is durable, water resistant and highly wear and U.V. resistance. It's extra thick film forming ability and properties enable **Ezycoat Corsa** to maintain excellent transpiration properties.

APPLICATION

Prior to application of the **Ezycoat Textured Paint Finishes** on to a surface it is essential that the surface be free of any contaminants that may affect the performance of the textured paint system. The coating sequence must follow the application specification sequence in Table 1.



Table 1:- Ezycoat Textured Paint Finishes

Application Specification Sequence over Ezycoat Render

Coating Sequence	Product
Coating 1.	1 Coat Ezycoat Ultrafine Sealer Drying time 2 hrs
Coating 2.	1 st Coat Ezycoat Corsa Drying time before recoat 5-6 hrs depending on weather conditions
Coating 3.	2 nd Coat Ezycoat Corsa Full cure at 12 Hours after completion depending on weather conditions.

** With some darker colours it may be necessary to apply a coat of Ezycoat Membrane in order to Maintain long term colour. This will be at the discretion of the Painting Contractor to determine or if in doubt contact our offices for further advice.*

It is recommended that the process of cutting in, be carried out at the same time as rolling the **Ezycoat Corsa** on the walls so as to maintain a wet on wet application. This will reduce the effect of roller marks on the wall. Always try to apply **Ezycoat Corsa Ezycoat** in shaded areas out of direct sunlight.

Table 2 – Ezycoat Corsa Properties Table

Consumption 15 Lit. Pail	30 to 35 sqm	Application by long nap roller followed with woolen Mit.
Base	Water	Wash up in water
Curing Time	12 Hrs	Depending on weather conditions
Colour	various	Colours available on request
Classification	Non Hazardous	

Due to the many different proprietary building systems available on the market, it is highly recommended that you contact our offices and request a copy of the Ezycoat specification for the building system you are using. **EZYBUILD SPECS** are readily available upon request either from our company representatives or our offices.

For more detailed information with regards this product and any safety concerns, please refer to the Material Safety Data Sheets available from Active Building Systems Pty Ltd upon request.

Note:

Ezycoat Corsa should not be applied at temperatures below 7°C or when there is the possibility of rain. The durability of the product in its original confection is guaranteed for 1 year as long as it is not exposed to direct sunlight or temperatures below 4 degrees.

Ezycoat Corsa is not suitable for use in areas prone to water logging, submersion, continually damp and/or below ground. Walls where **Ezycoat Corsa** is to be applied must be free draining. In the case of retaining walls the rear of the wall must be engineered to prevent any penetration of moisture or water through the wall in to the rear of the **Ezycoat Corsa**. Failure to do so will result in damage to the **Ezycoat Corsa** and is not covered by warranty.

For more detailed information with regards this product and safety issues, please refer to the Material Safety Data Sheets available from Active Building Systems Pty Ltd upon request.

Ezycoat Corsa are to be applied only by trades persons holding a license for this trade as recognised by the legislative building authority for the relevant state to which the work is being carried out. Misuse of this product and/or non compliance with technical specifications will void any warranties whether verbal or written.

Active Building Systems Pty Ltd reserves the right to change, update and republish these specifications without any notice. It is the user's responsibility to attain the most current publication of Ezycoat Specifications from Active Building Systems Pty Ltd.

