

EZYCOAT FINE FINISH**DESCRIPTION AND COMPOSITION**

Ezycoat Fine Finish is manufactured from the highest quality of raw materials available on the global market. It is essentially a full acrylic fine render that contains fillers and binders of the highest quality integrated with a very fine extensively graded quartz sand that makes it ideal for thin section rendering on a variety of cladding mediums. Its high volume of Pigment makes it ideal for tinter acceptance and colour control. Its very fine quartz makeup allows it produce a finish on a variety of surfaces that were once only possible it simulate with a traditional scrub fine render finish.

This product has been specifically designed to achieve certain qualities which cannot be attained by dry mix modified cement render such as the Ezycoat EzySkim Render ,Ezypump, ECA and Ezycoat Super 6 . (Sometimes referred to as mineral based renders). **Ezycoat Fine Finish** is a one part product that once mixed is ready for immediate use straight from the pail. It produces a consistent scrub fine render like finish with excellent adhesion and flexibility and can be applied to thickness of 1.0 to 1.5 mm in any 1 application.

USE

Ezycoat Fine Finish has been designed to produce a highly decorative external synthetic finish which is suitable for application to a variety of surfaces that would not normally accept a traditional render or modified skim render. **Ezycoat Fine Finish** is ideally suited for application over propriety installed Fibre cement sheeted surfaces. Its ability to adhere to smooth surfaces and its flexible nature make it suitable for this type of application. It also suitable for use as a finish over existing traditional rendered or Ezycoat EzySkim Render ,Ezypump, ECA and Ezycoat Super 6 surfaces.

When applying **Ezycoat Fine Finish** to any surface it is recommended that the surfaces be free of any contaminant which may affect the performance of the coatings and that any visible imperfections in the surface which may be transferred through to the finished surface be patched using Ezycoat Coarse or Smooth Patch.(see Ezycoat Coarse Patch and Smooth Patch Technical Data sheets TDS. for further advice.)

APPLICATION

Once having provided a uniform flat substrate, apply a base coat of Ezycoat Masonry Sealer (see Ezycoat Masonry Sealer Technical Data Sheet for further advice.) maintaining even coverage. Then allow the treated surface to stand for approximately 1 hour, prior to applying **Ezycoat Fine Finish**. Using a stainless steel plasterer's trowel, evenly spreading the **Ezycoat Fine Finish** over the surface.

Depending on the surface to be coated, it may be necessary to apply the **Ezycoat Fine Finish** in 2 coats. The first being the leveling coat which will be left as a float finish and the second the finishing coat. The finishing coat may either be finished flat with a plastic trowel or lightly sponged off to provide a sandy finish to the surface, however this will depend on the desired finish that is specified. For Surfaces that require that additional build thickness we recommend the first coat be Ezycoat Polymer Render (see Ezycoat Polymer Render TDS.) with the 2nd as Ezycoat Fine Finish.

Two coats of Ezycoat Membrane paint is then applied in accordance with the Ezycoat Membrane specifications, 48 hrs after the application of the **Ezycoat Fine Finish**. This will complete the application process, producing a durable and aesthetically pleasing finish.

DATA

Consumption:	2 Coat - 12 to 14 sqm. per 15 Lit. 1 Coat - 15 sqm. per 15 Lit. (may vary depending on surface)
Pail Size:	15Lit.
Classification:	non-dangerous goods
Colours:	Tintable Base
Important Notes:	Do not apply in temperatures below 10 degrees Celsius or 24 hrs prior to or after wet & rainy conditions. Do not apply in moist conditions. All walls must be free of moisture prior to application. All surfaces should be cleaned and free of any contaminant, releasing agent, fungal growth which may affect the performance of these coatings. Any imperfections which may become visible in the finished surface should be patched and leveled with Ezycoat Patching compounds. Any structural imperfections and/or cracks will need to be stabilised prior to any further applications. The durability of the product in its original confection is guaranteed for 1 year as long as it is not exposed to direct sunlight or temperatures below 6 degrees. Ezycoat Fine Finish is not suitable for use in areas prone to water logging submersion, continually damp and/or below ground. Walls where Ezycoat Fine Finish is to be applied must be free draining. In the case of retaining walls the rear of the wall must be engineered to prevent any penetration of moisture or water through the wall in to the rear of the Ezycoat Fine Finish. Failure to do so will result in damage to the Ezycoat Fine Finish and is not covered by warranty. Excess Waste product should be disposed of in responsible manner following guidelines as set out by the local council's by-laws and Waste Disposal Procedures.

APPLICATION SEQUENCE & SPECIFICATIONS

Due to the many different proprietary building systems available on the market, it is highly recommended that you contact our offices and request a copy of the Ezycoat specification for the building system you are using. **EZYBUILD SPECS** are readily available upon request either from our company representatives or our offices.

For more detailed information with regards this product and any safety concerns, please refer to the Material Safety Data Sheets available from Active Building Systems Pty Ltd upon request.

Ezycoat Fine Finish is to be applied by suitably licensed persons holding a license for this trade as recognised by the legislative building authority for the relevant state to which the work is being carried out. Misuse of this product and/or non compliance with technical specifications will void any warranties verbal or written. Active Building Systems Pty Ltd reserves the right to change, update and republish these specifications without any notice. It is the user's responsibility to attain the most current publication of Ezycoat Specifications from Active Building Systems Pty Ltd.

