

EZYCOAT MONACO**DESCRIPTION AND COMPOSITION**

Ezycoat Monaco is an acrylic texture finish. It consists of a fine grade of quartz fillers mixed a granular coarse marble with binders integrated with in a mixture of acrylic emulsion and pigments. This decorative granular finish emulates a unique texture finish with random but consistent pattern of texture. **Ezycoat Monaco** replicates a refined yet individual finish which provides the versatility in extending the decorative finish parameters. **Ezycoat Monaco** joins the range of decorative finishes such as Ezycoat Scratch & Ezycoat Polymer to provide a product that has been specifically designed as a top coat to various cementious render and skim rendered surfaces. Its textured appearance makes it attractive for use over a variety of fibre cement cladding systems and precast concrete surfaces. **Ezycoat Monaco** is a one part product that once mixed is ready for immediate use straight from the pail. The granular particles allow **Ezycoat Monaco** to be troweled on in a one coat application.

USE

Ezycoat Monaco has been designed to produce a highly decorative external synthetic finish which is suitable for application to a variety of surfaces that would not normally accept a traditional render or modified skim render. **Ezycoat Monaco** is ideally suited for application over propriety installed Fibre cement sheeted surfaces. Its ability to adhere to smooth surfaces and its flexible nature make it suitable for this type of application. It also suitable for use as a finish over existing traditional rendered or Ezycoat EzySkim Render ,Ezypump, ECA and Ezycoat Super 6 surfaces.

When applying **Ezycoat Monaco** to any surface it is recommended that the surfaces be free of any contaminant which may affect the performance of the coatings and that any visible imperfections in the surface which may be transferred through to the finished surface be patched using Ezycoat Coarse or Smooth Patch.(see Ezycoat Coarse Patch and Smooth Patch Technical Data sheets for further advice.)

APPLICATION

Once having provided a uniform flat substrate, apply a base coat of Ezycoat Hi Opacity or Masonry Sealer (see Ezycoat Hi Opacity & Masonry Sealer Technical Data Sheet for further advice.) always maintaining even coverage. Then allow the treated surface to stand for approximately 1 hour, prior to applying **Ezycoat Monaco**. Using a stainless steel plasterer's trowel, evenly spreading the **Ezycoat Monaco** over the surface.

In most cases **Ezycoat Monaco** may be applied in a single coat application providing an adequate base has been provided. The application process involves troweling out the **Ezycoat Monaco** straight from the pail onto the suitably prepared surface. Once leveled off tightly with a stainless steel trowel the product should then be floated over using a polystyrene float. This will allow the textured granules within the **Ezycoat Monaco** to create the unique texture finish. Once a texture has been achieved the surface should then be flattened off and finished using a plastic trowel. Two coats of Ezycoat Membrane paint is then applied in accordance with the Ezycoat Membrane specifications, 48 hrs. after the application of the **Ezycoat Monaco**. This will complete the application process, producing a durable and aesthetically pleasing finish.

DATA

Consumption:	1 Coat - 10 to 12 sqm. per 15 Lit.
Pail Size:	15Lit.
Classification:	non-dangerous goods
Colours:	White other colours available on request
Important Notes:	Do not apply in temperatures below 10 degrees Celsius or 24 hrs prior to or after wet & rainy conditions. Do not apply in moist conditions. All walls must be free of moisture prior to application. All surfaces should be cleaned and free of any contaminant, releasing agent, fungal growth which may affect the performance of these coatings. Any imperfections which may become visible in the finished surface should be patched and leveled with Ezycoat Patching compounds. Any structural imperfections and/or cracks will need to be stabilised prior to any further applications. The durability of the product in its original confection is guaranteed for 1 year as long as it is not exposed to direct sunlight or temperatures below 6 degrees. Ezycoat Monaco is not suitable for use in areas prone to water logging, submersion, continually damp and/or below ground. Walls where Ezycoat Monaco is to be applied must be free draining. In the case of retaining walls the rear of the wall must be engineered to prevent any penetration of moisture or water through the wall in to the rear of the Ezycoat Monaco. Failure to do so will result in damage to the Ezycoat Monaco and is not covered by warranty. Excess Waste product should be disposed of in responsible manner following guidelines as set out by the local council's by-laws and Waste Disposal Procedures.

APPLICATION SEQUENCE & SPECIFICATIONS

Due to the many different proprietary building systems available on the market, it is highly recommended that you contact our offices and request a copy of the Ezycoat specification for the building system you are using. **EZYBUILD SPECS** are readily available upon request either from our company representatives or our offices.

For more detailed information with regards this product and any safety concerns, please refer to the Material Safety Data Sheets available from Active Building Systems Pty Ltd upon request.

Ezycoat Monaco is to be applied by suitably licensed persons holding a license for this trade as recognised by the legislative building authority for the relevant state to which the work is being carried out. Misuse of this product and/or noncompliance with technical specifications will void any warranties whether verbal or written. Active Building Systems Pty Ltd reserves the right to change, update and republish these specifications without any notice. It is the user's responsibility to attain the most current publication of Ezycoat Specifications from Active Building Systems Pty Ltd.

