

# EZYCOAT

RENDER • TEXTURE • PAINT

## RENDER RANGE GUIDE



**EZYCOAT**  
RENDER • TEXTURE • PAINT

### ECA RENDER

Suitable for application on clay brick, concrete block, masonry surfaces and EPS systems.

- » Polymer modified for superior bonding strength
- » Excellent cured strength
- » Easy to apply



EZRX2600-20KG

20 kg

**EZYCOAT**  
RENDER • TEXTURE • PAINT

### PUMP RENDER

Suitable for application on clay brick, concrete block, masonry surfaces.

- » Premium premix cement render
- » Excellent cured strength
- » Pump or hand application



EZRX2600-20KG

20 kg

**EZYCOAT**  
RENDER • TEXTURE • PAINT

### EZYPREP & PATCH

Suitable for application on clay brick, concrete block, masonry surfaces.

- » Excellent cured strength
- » Polymer modified for ease of use



EZRX2600-20KG

20 kg



Stock image used, final product finish may differ

# EZYCOAT RENDER RANGE

PRODUCT	APPLICATION TOOLS	FEATURE/BENEFIT	SAND GRADE	COVERAGE	RECOMMENDED COATING THICKNESS	POST APPLICATION
 <b>SKIM RENDER</b> Off White	Hawk & Steel Trowel Render Pump Sponge Float	Provides an even and consistent sand finish for use as a skim coat.	Medium Fine	3 - 4.8 m <sup>2</sup> /bag	2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm	48 hour set time 7 day cure Max strength at 28 days
 <b>ECA RENDER</b> Off White	Hawk & Steel Trowel Render Pump Sponge Float	Designed for multi-purpose use including EPS systems, with the addition of polymer for superior bonding strength.	Medium Fine	3 - 4.8 m <sup>2</sup> /bag	2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm	48 hour set time 7 day cure Max strength at 28 days
 <b>PUMP RENDER</b> Off White	Hawk & Steel Trowel Render Pump Sponge Float	Developed to cater for both hand and pump application.	Medium Coarse	3 - 4.8 m <sup>2</sup> /bag	2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm	48 hour set time 7 day cure Max strength at 28 days
 <b>EZYFLOAT RENDER</b> Off White	Hawk & Steel Trowel Sponge Float	Ideal for use under acrylic texture coatings.	Coarse	3 - 4.8 m <sup>2</sup> /bag	2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm	48 hour set time 7 day cure Max strength at 28 days
 <b>EZYPREP &amp; PATCH</b> Off White	Steel Trowel	To prep and patch surfaces that would otherwise not accept a render product.	Fine	4 - 6 m <sup>2</sup> /bag	1.5mm MIN 3mm MAX	48 hour set time 7 day cure Max strength at 28 days

For further information visit [activebuildingsystems.com.au](http://activebuildingsystems.com.au)  
 or call **1300 566 592**