

EZYCOAT

RENDER • TEXTURE • PAINT

RENDER RANGE GUIDE







EZYCOAT
RENDER • TEXTURE • PAINT

ECA RENDER

Suitable for application on clay brick, concrete block, masonry surfaces and EPS systems.

- Polymer modified for superior bonding strength
- Excellent cured strength
- Easy to apply


EZRK2600-20KG
20 kg


EZYCOAT
RENDER • TEXTURE • PAINT

PUMP RENDER

Suitable for application on clay brick, concrete block, masonry surfaces.

- Premium premix cement render
- Excellent cured strength
- Pump or hand application


EZRK2600-20KG
20 kg









EZYCOAT
RENDER • TEXTURE • PAINT

EZYPREP & PATCH

Suitable for application on clay brick, concrete block, masonry surfaces.

- Excellent cured strength
- Polymer modified for ease of use
- Reduces construction costs


EZRK2600-20KG
20 kg

Stock image used, final product finish may differ

EZYCOAT RENDER RANGE

| PRODUCT | APPLICATION TOOLS | FEATURE/BENEFIT | SAND GRADE | COVERAGE | RECOMMENDED COATING THICKNESS | POST APPLICATION |
|--|--|---|---------------|-----------------------------|--|---|
|  <p>SKIM RENDER Off White</p> | Hawk & Steel Trowel Render Pump Sponge Float | Provides an even and consistent sand finish for use as a skim coat. | Medium Fine | 3 - 4.8 m ² /bag | 2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm | 48 hour set time 7 day cure Max strength at 28 days |
|  <p>ECA RENDER Off White</p> | Hawk & Steel Trowel Render Pump Sponge Float | Designed for multi-purpose use including EPS systems, with the addition of polymer for superior bonding strength. | Medium Fine | 3 - 4.8 m ² /bag | 2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm | 48 hour set time 7 day cure Max strength at 28 days |
|  <p>PUMP RENDER Off White</p> | Hawk & Steel Trowel Render Pump Sponge Float | Developed to cater for both hand and pump application. | Medium Coarse | 3 - 4.8 m ² /bag | 2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm | 48 hour set time 7 day cure Max strength at 28 days |
|  <p>TRADITIONAL RENDER Off White</p> | Hawk & Steel Trowel Render Pump Sponge Float | A versatile and easy to use render with similar properties to traditional sand cement render. | Coarse | 3 - 4.8 m ² /bag | 2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm | 48 hour set time 7 day cure Max strength at 28 days |
|  <p>EZYFLOAT RENDER Off White</p> | Hawk & Steel Trowel Sponge Float | Ideal for use under acrylic texture coatings. | Coarse | 3 - 4.8 m ² /bag | 2.5mm MIN - 5mm MAX per coat to a MAX thickness of 8mm | 48 hour set time 7 day cure Max strength at 28 days |
|  <p>EZYPREP & PATCH Off White</p> | Steel Trowel | To prep and patch surfaces that would otherwise not accept a render product. | Fine | 4 - 6 m ² /bag | 1.5mm MIN 3mm MAX | 48 hour set time 7 day cure Max strength at 28 days |
|  <p>HIGH BUILD 40 RENDER Off White</p> | Steel Trowel | Used on surfaces that require additional build thickness. | Coarse | 0.5 - 1 m ² /bag | 10mm MIN 20mm MAX | 48 hour set time 7 day cure Max strength at 28 days |

For further information visit activebuildingsystems.com.au
or call **1300 566 592**